

Serial No.: 10/712,260
Atty. Docket No.: P69290US0

IN THE CLAIMS:

Please amend the claims as follows:

1. (Currently Amended) A method for one-piece injection moulding of a soft needle catheter having a hub and a tube-shaped flexible part both formed by said one-piece injection moulding, comprising the steps of:

feeding a molten polymer into a mould having a core which is used to form an interior of said catheter, the mould and the core together defining a hub cavity to form said hub and a tube-shaped cavity ~~having a cylindrical part~~ to form said tube-shaped flexible part[[,]];

said feeding step including using a core having a cone-shaped part that extends from the hub cavity into the tube-shaped cavity and a cylindrical part extending from a distal end of said cone-shaped part to create within said tube-shaped cavity a tube-shaped flexible part having a cylindrical portion formed distal from said hub and a cone-shaped portion extending cone-shaped part between said hub cavity and said cylindrical ~~part~~ portion;

removing the core from the catheter when the polymer has been sufficiently cured for the core to be removed; and

Serial No.: 10/712,260
Atty. Docket No.: P69290US0

removing the one-piece injection moulded soft needle catheter from the mould when the polymer has been sufficiently cured to be removed.

2. (Previously Presented) The method according to claim 1, wherein the catheter is cured to its final state in the mould.

3. (Previously Presented) The method according to claim 1, wherein the molten polymer is supplied to the mould via at least two inlets.

4. (Previously Presented) The method according to claim 3, wherein the inlets are placed at the hub forming part of the mould.

5. (Previously Presented) The method according to claim 1, wherein the mould separates along the axis of the tube-shaped part.

6. (Previously Presented) The method according to claim 1, wherein the mould separates perpendicular to the tube-shaped part and at or just below the hub.

Serial No.: 10/712,260
Atty. Docket No.: P69290US0

7. (Previously Presented) The method according to claim 1, wherein the polymer is chosen from the group consisting of polyester ethers, styrene based TPE, olefin based TPE, urethane based TPE, ester based TPE, amid based TPE polyolifines and silicone rubbers.

8. (Previously Presented) The method according to claim 1, wherein the polymer is selected from the group consisting of polypropylene, thermoplastic elastomers, mixtures of thermoplastic elastomers and polypropylene, low density polyethylenes, and thermoplastic polyurethane elastomers.

9. (Previously Presented) The method according to claim 1, wherein the polymer has a shore between 40 and 60D.

10. (Previously Presented) The method according to claim 1, wherein more than one polymer is used in the method.

Claims 11-23 (Canceled).

Serial No.: 10/712,260
Atty. Docket No.: P69290US0

24. (Previously Presented) The method according to claim 3, wherein the inlets are placed symmetrically around an axis of the core.